

#### PRODUCT DESCRIPTION:

5108 Fast-Drying Polyaspartic is designed as a 72% solids topcoat allowing for extended working times, easier application, and quicker return to service due to its lower viscosity. It features good abrasion and chemical resistance for light to medium duty environments.

#### APPLICATIONS:

- Residential Floors
- Commercial Floors
- Industrial Floors
- Exterior Applications

#### ADVANTAGES:

- High-Build
- Low VOC
- High-Gloss
- Non-Yellowing
- Good Resistance to most Chemicals

#### LIMITATIONS:

- Requires Moisture Vapor Primer for on-grade slabs with MVE of 3 Lbs or higher
- Will not bridge cracking
- Not resistant to strong acids
- 5108 is combustible so all sources of ignition should be shut off and proper ventilation should be used

#### COLORS:

CLEAR

#### COVERAGE RATES:

OVER CONCRETE SUBSTRATE		
1 <sup>ST</sup> COAT	200 FT <sup>2</sup> / GAL @ 8 MILS WET FILM	
2 <sup>ND</sup> COAT	250 FT <sup>2</sup> / GAL @ 6.4 MILS WET FILM	
OVER FLAKE SYSTEM		
1/4" FLAKE	1/8" FLAKE	1/16" FLAKE
200 FT <sup>2</sup> / GAL	150 FT <sup>2</sup> / GAL	125 FT <sup>2</sup> / GAL

#### TECHNICAL PROPERTIES:

VOLUMETRIC MIX RATIO	1A:1B	
VOLUMETRIC SOLIDS	72%	
VOC	<50 g/L	
POTLIFE (1.5 GAL MASS)	35 Mins @ 75°F	
WORKING TIME	30 Mins @ 75°F	
DRY TO TOUCH	3-4 Hours @ 75°F	
RECOAT WINDOW	4-8 Hours	
FULL CURE	5-7 Days	
SHORE D HARDNESS	ASTM D2240	75-80
ABRASION RESISTANCE	ASTM D4060	9 mg Lost
ADHESION	ACI 503R	300 PSI
FLAMMABILITY	COMBUSTIBLE	

#### CHEMICAL RESISTANCE:

ACETONE	NO EFFECT
XYLENE	NO EFFECT
10% HCL	NO EFFECT
AMMONIA	NO EFFECT
DEGREASER	FAINT SPOTTING
LIQUID PLUMMER	NO EFFECT
VINEGAR	NO EFFECT
CLOROX	NO EFFECT
WINDEX	NO EFFECT
MOTOR OIL	NO EFFECT
GASOLINE	NO EFFECT
SKYDROL	NO EFFECT
HOT TIRE	NO EFFECT

#### PACKAGING:

2 Gallon Kit	10 Gallon Kit
--------------	---------------

#### STORAGE:

Store materials indoors between 50°F & 75°F




#### SHELF LIFE:

One year from date of manufacture

#### APPLICATION EQUIPMENT:





Protective Clothing	<b>18" Roller Frame</b> SKU - 7012
Jiffy Mixing Paddle SKU - 7050	<b>18"x3/8" Nap Roller Cover</b> SKU - 7006-1
Slow Speed Drill	<b>8-12 mil Notched Squeegee</b> SKU - 7090-K
Spike Shoes SKU - 7045-D	<b>Magic Trowel</b> SKU - 7071-22

SUBSTRATE REQUIREMENTS:	
<b>CONCRETE:</b>	Concrete must be structurally sound and free of all dirt, debris, and contaminants
<b>PROFILE:</b>	Concrete shall be porous and have a Concrete Surface Profile (CSP) level between 2 & 4
<b>MOISTURE:</b>	Substrate shall have Moisture Vapor Emission Rate (MVER) of 3lbs / 1000 ft <sup>2</sup> / 24 hr. or less
<b>TEMPERATURE:</b>	Ambient and substrate temps must be above 35°F and Relative Humidity should not exceed 65%

SURFACE PREPARATION:	
	<b>Perform Moisture Test</b> using Calcium Chloride concrete moisture test kit per ASTM F1869 1 test/1000 ft <sup>2</sup> is recommended.
	<b>Patch</b> all depressions, divots and cracks using 4900 5-minute Crack Weld, 4930 Polyurea Crack & Spall Filler, or Divot Patch to reduce the ability to see the defect through the epoxy coating.
	<b>Concrete</b> should be mechanically profiled and prepared to produce a Concrete Surface Profile (CSP) level between #2 & #4 according to the (ICRI) Guideline No. 03732.





**PLEASE REVIEW SAFETY DATA SHEETS (SDS) & CHEMICAL SAFETY GUIDE FOR SAFETY AND PRECAUTIONS**

ENVIRONMENTAL FACTORS:
Working times are affected by environmental conditions. Large masses of mixed and/or heated material will have shorter pot-life. Keep material core temps between 50-75°F. In elevated temps consider icing buckets to reduce product temps and cold climates use pail warmers

5108 MIXING STEPS:	
	<b>Pour pre-mixed A-Component and B-Component</b> into a clean 5-gallon bucket (If mixing bulk kit be sure to follow specified 1A:1B ratio)
	<b>Mix A &amp; B Components</b> using drill at slow speed for 2 minutes
	<b>Transfer mix to new mixing vessel</b>
	<b>Continue to mix</b> for an additional 30 seconds to ensure components are thoroughly blended.

5108 APPLICATION STEPS:		
COVERAGE RATES OVER CONCRETE SUBSTRATE:		
1 <sup>ST</sup> COAT	200 FT <sup>2</sup> / GAL @ 8 MILS WET FILM	
2 <sup>ND</sup> COAT	250 FT <sup>2</sup> / GAL @ 6.4 MILS WET FILM	
OVER FLAKE SYSTEM		
<b>1/4" FLAKE</b>	<b>1/8" FLAKE</b>	<b>1/16" FLAKE</b>
200 FT <sup>2</sup> / GAL	150 FT <sup>2</sup> / GAL	125 FT <sup>2</sup> / GAL

#### APPROXIMATE WORKING TIMES: 30 MINS @ 75°F

	<b>Pour a band</b> of mixed material out onto the floor roughly 6-8" wide
	<b>Begin spreading</b> with an 8-12 mil notched squeegee or Magic Trowel. Work material evenly keeping a wet edge
	<b>Perform a Single Backroll</b> on the surface by walking into the wet material wearing spike shoes and roll perpendicular to your first direction of application.
	<b>Allow system to dry</b> typically 3-4 hours at 75°F

#### CLEAN-UP:

Immediately clean up splatter marks and tools with MEK or Acetone. Clean hands and exposed skin with mild soap and water, and/or citrus based hand cleaner.

#### MAINTENANCE:

Maintain 5108 to minimum of 4 mils dry film.

#### DISCLAIMER:

All information provided in this technical data sheet is based on laboratory data. It is the responsibility of the customer to test the material for their application and conditions prior to using the product.

#### TEMPERATURE:

The product was tested at ambient temperature (75°F -77°F). Results WILL vary when product is used at temperatures different from testing temperature. The pot life, gel time, and cure time is generally longer for colder temperature applications, and shorter for higher temperature applications. Physical properties are also impacted and dependent upon temperature.

#### SLIP RESISTANCE:

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Versatile High-Performance Coatings recommend the use of angular slip resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily, or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Versatile High-Performance Coatings or its sales agents will not be responsible for injury incurred in a slip and fall accident

#### WARRANTY:

Versatile High-Performance Coatings guarantees that this product is free from manufacturing defects and complies with our published specifications. If the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. Versatile High-Performance Coatings (herein referred to as "seller") makes no warranty, expressed or implied, regarding the use of its products. Since use of this product is beyond the seller's control, the buyer assumes all risk of use. Seller's obligation shall be to replace material if found defective. Seller shall not be liable for any damage, injury, loss, direct or consequential, resulting from the use of its products. End user must determine if substrate is suitable for coating application before installing.

#### TECHNICAL SERVICES:

Technical services can be obtained by contacting Versatile High-Performance Coatings directly at 214-807-6878.